



Technical Data Sheet

Product	TW340 Sheen Series			
Description	Aquatech WB Bi-Component Clear Topcoat			
Color	Clear			
Chemical-physical Properties				
CODE	Density (Kg/l)	Density (lb/US gal)	Solid content %	
TW340	1,030 ± 0,030	8,6 ± 0,3	31,4 ± 2	
TW341	1,029 ± 0,030	8,6 ± 0,3	32,2 ± 2	
TW342	1,028 ± 0,030	8,6 ± 0,3	31,6 ± 2	
TW343	1,031 ± 0,030	8,6 ± 0,3	32,3 ± 2	
TW344	1,034 ± 0,030	8,6 ± 0,3	32,6 ± 2	
TW346	1,037 ± 0,030	8,7 ± 0,3	33,7 ± 2	
TW347	1,050 ± 0,030	8,8 ± 0,3	36,4 ± 2	
	Viscosity (Ford 6 cup)	45 ± 4		
USAGE INDICATIONS				
The product, after careful mixing, is ready to use				
READY TO USE PRODUCT PROPERTIES (AVERAGE)				
Code/Sheen	CODE	Sheen level EN ISO 2813 (angle measurement 60°)		
		applied micron: 150		
		Wet Mils: 5,9		
	TW340	Sheen	78 ± 5	
	TW341	Sheen	60 ± 4	
	TW342	Sheen	48 ± 3	
	TW343	Sheen	30 ± 2	
	TW344	Sheen	20 ± 2	
TW346	Sheen	10 ± 1		
TW347	Sheen	5 ± 1		
Application	Airmix spray	Quantities		
		gr/m ² min-max:	110 - 140	
	Hand spray	Wet Mils min-max	4,2 - 5,4	
		gr/m ² min-max:	110 - 140	
	Wet Mils min-max	4,2 - 5,4		



PRODUCT PROPERTIES AFTER APPLICATION				
Drying	Room temperature drying (18-22°C / 64 – 72°F e 65-70% relative humidity) complete drying		40 h	
	Dust free		40 min	
	Touch dry		55 min	
	Hard dry		4 h	
	Stackable after room temperature drying		24 h (with spacers)	
	Laminar flow cabinet drying		Temp°C	35
			Temp°F	95
			Air speed m/sec	1,5
			Air speed ft/sec	4,9
	Stackable after jet hot air drying		4 h (with spacers)	
Additional products		Quantities		
Hardener	TXW14	In weight w/w %	10	
		In volume v/v %	9,8	
	Solid content %	69,0 ± 2		
READY TO USE PRODUCT PROPERTIES (AVERAGE)				
	Solid content 1st + 2nd component (%)		34,8 ± 2	
	Pot-Life - mixture (maximum pot-life of the product prepared according to usage indications)		3 h	
	Viscosity (Ford 6 cup)		55 ± 4	
Code/Sheen	CODE		Sheen level EN ISO 2813 (angle measurement 60°)	
			applied micron: 150	
			Wet Mils: 5,9	
	TW340	Sheen	80 ± 5	
	TW341	Sheen	65 ± 4	
	TW342	Sheen	50 ± 3	
	TW343	Sheen	30 ± 2	
	TW344	Sheen	22 ± 2	
TW346	Sheen	10 ± 1		
TW347	Sheen	5 ± 1		
Application			Quantities	
	Airmix spray	gr/m ² min-max:	110 - 140	
		Wet Mils min-max	4,2 - 5,3	
	Hand spray	gr/m ² min-max:	110 - 140	
Wet Mils min-max		4,2 - 5,3		



PRODUCT PROPERTIES AFTER APPLICATION				
Drying	Room temperature drying (18-22°C / 64 – 72°F e 65-70% relative humidity) complete drying		48 h	
	Dust free		50 min	
	Touch dry		65 min	
	Hard dry		5 h	
	Stackable after room temperature drying		24 h (with spacers)	
	Laminar flow cabinet drying		Temp°C	35
			Temp°F	95
			Air speed m/sec	1,5
			Air speed ft/sec	4,9
	Stackable after jet hot air drying		4 h (with spacers)	
Additional products		Quantities		
Properties	Non flammable hardener			
Hardener	TXW14	In weight w/w %	10	
		In volume v/v %	9,6	
	Solid content %	70,0 ± 2		
READY TO USE PRODUCT PROPERTIES (AVERAGE)				
	Solid content 1st + 2nd component (%)		34,9 ± 2	
	Pot-Life - mixture (maximum pot-life of the product prepared according to usage indications)		2 h	
	Viscosity (Ford 8 cup)		40 ± 3	
Code/Sheen	CODE		Sheen level EN ISO 2813 (angle measurement 60°)	
			applied micron: 150	
			Wet Mills: 5,9	
	TW340	Sheen	85 ± 5	
	TW341	Sheen	70 ± 4	
	TW342	Sheen	55 ± 4	
	TW343	Sheen	35 ± 2	
	TW344	Sheen	25 ± 2	
	TW346	Sheen	15 ± 1	
TW347	Sheen	5 ± 1		



Application		Quantities	
Airmix spray	gr/m ² min-max:	110	- 140
	Wet Mills min-max	4,2	- 5,3
Hand spray	gr/m ² min-max:	110	- 140
	Wet Mills min-max	4,2	- 5,3
PRODUCT PROPERTIES AFTER APPLICATION			
Drying			
Room temperature drying (18-22°C / 64 – 72°F e 65-70% relative humidity) complete drying		48 h	
Dust free		50 min	
Touch dry		65 min	
Hard dry		5 h	
Stackable after room temperature drying		24 h (with spacers)	
Laminar flow cabinet drying		Temp°C	35
		Temp°F	95
		Air speed m/sec	1,5
		Air speed ft/sec	4,9
Stackable after jet hot air drying		120 min	
Stackable after jet hot air drying		4 h (with spacers)	
Additional products		Quantities	
Properties	Hardener useful to reduce COV values during application (<50g/L)		
Hardener	HXS5A16	In weight w/w %	10
		In volume v/v %	9,4
Solid content %		99,9 ± 2	
Thinner	Water	In weight w/w %	5
		In volume v/v %	5
READY TO USE PRODUCT PROPERTIES (AVERAGE)			
Solid content 1st + 2nd component (%)		37,6 ± 2	
Pot-Life - mixture (maximum pot-life of the product prepared according to usage indications)		2 h	
Viscosity (Ford 8 cup)		50 ± 4	

AUSTRALIAN DISTRIBUTOR

Superior Timber Coatings

Unit 13, 257 Colchester Road Kilsyth (Vic) 3137 Ph.

03 9761 6899 Emergency Mob: 0410 635 016

www.sales@stcoatings.com.au

Unit 2, 13 Thames Avenue Klemzig (S. Aust.) 5087

Ph. 08 7099 3659 Emergency Mob: 0410 635 016

www.saleessa@stcoatings.com.au

Website: superiortimbercoatings.com.au



Code/Sheen	CODE	Sheen level EN ISO 2813 (angle measurement 60°)				
		applied micron: 150				
		Wet Mils: 5,9				
	TW340	Sheen	85	±	5	
	TW341	Sheen	70	±	4	
	TW342	Sheen	55	±	4	
	TW343	Sheen	35	±	2	
	TW344	Sheen	25	±	2	
	TW346	Sheen	15	±	1	
	TW347	Sheen	5	±	1	
Application	Quantities					
	Airmix spray	gr/m ² min-max:	110	-	140	
		Wet Mils min-max	4,2	-	5,3	
	Hand spray	gr/m ² min-max:	110	-	140	
Wet Mils min-max		4,2	-	5,3		
PRODUCT PROPERTIES AFTER APPLICATION						
Drying	Room temperature drying (18-22°C / 64 – 72°F e 65-70% relative humidity) complete drying		48 h			
	Dust free		50 min			
	Touch dry		75 min			
	Hard dry		5 h			
	Stackable after room temperature drying		24 h (with spacers)			
	Laminar flow cabinet drying		Temp°C	35		
			Temp°F	95		
			Air speed m/sec	1,5		
			Air speed ft/sec	4,9		
	Stackable after jet hot air drying		120 min			
Stackable after jet hot air drying		4 h (with spacers)				
Shelf life	12 months after production					
SPECIFIC WARNINGS	<p>If required, thin with water up to 5% (maximum)</p> <p>Water-based products viscosity values tend to alter during storage The value indicated in this technical data sheet is the one measured during quality control</p>					



WARNINGS

In a coating process with professional products:

- besides the product quality, the final result also depends on numerous other variables, such as environmental conditions; homogeneity in the quality of the support; the constancy of the application cycle; the plants performance; the proper use of the product, etc.
- in the process of industrial coating a certain waste of product is to be considered normal and therefore not attributable to product quality
- The final colour is influenced by quality and the preparation of the support and the conditions of application, for this reason it is essential to check in advance the result in terms of final use

Our Company cannot ensure the control of the coating process carried out by the user. We cannot, therefore, take on any responsibility for the final result achieved through the use of our products. On the other hand, we guarantee the consistency of the chemical and physical characteristics of the product indicated in the relevant Technical Data Sheet, pledging to replace it if it does not correspond to the declared features. Data on the chemical and physical characteristics of the product are recorded at 20°C / 68°F and 70% R.U.

For best results, the optimum conditions of application are:

- Ambient temperature between 18 and 22°C (64 - 72 °F)
- ambient relative humidity between 65 and 70%
- support humidity between 8 and 14%

The conditions to be observed scrupulously are:

- Water-based products are particularly sensitive to storage conditions: temperatures below 5 °C / 41°F and above 35 °C / 95°F may affect the product, characteristics, making it unusable. For this reason, a water-based product should be stored indoors at temperatures not below 5 °C / 41°F and not above 35 °C / 95°F, in a properly ventilated place, not exposed to solar radiation
- Always shake the products well before use
- Before use, always shake well the product mixed with any other components such as catalysts, accelerators, thinners
- The application must not take place at a temperature lower than 15 °C / 59°F or above 30 °C / 86°F
- The drying should not take place at a temperature below 15 °C / 59°F
- The ambient relative humidity during drying should be between 50% and 70%
- To decant paints, exclusively use containers made of suitable material, such as polyethylene and stainless steel
- After use, we recommend that you always close the can carefully

The end result of the coating cycle is the sole responsibility of the users, who must make sure that the product matches their needs and that environmental conditions, application or media specifications do not require substantial changes of use

It is the user's responsibility:

- Adhere to the conditions indicated above
- comply with the rules of hygiene and safety during product application, according to the descriptions given in the safety data sheets
- for solvent-based products spark-proof equipment should be used
- It is forbidden to smoke while using the product

At the bottom of each sheet there is a date of validity

The Company invites you to check with their staff that the product data sheet in your possession is the most updated, since the characteristics of the products are subject to adjustments over time

For more information, please contact (see below):

Issue date: 2019-09

Rev.: 2